

TECHNICAL SPECIFICATIONS

C1S High bulky Ivory
 Ref.: 10783 - Ze.
 Origin: China

Basis Weight		Thickness		Stiffness (Taber 15°)	
g/m ² ±3%	24"x36"	µm (±4%)	pt (±4%)	mN·m (+0/-20%)	
	500 (lb)			CD	MD
215	132	310	12.2	4.4	8.8
235	144	355	14.0	5.5	11.0
250	154	380	15.0	7.5	14.3
270	166	415	16.3	9.0	17.6
295	181	460	18.1	12.1	24.8
325	200	510	20.1	16.1	31.4
350	215	560	22.0	18.7	38.5
380	233	610	24.0	22.0	44.0

Property	Unit	Value
PPS (Top)	µm	≤1.7
Moisture	%	6.0 ±1.5
Brightness (Top)	%	91 ±2
75°Gloss(Top)	%	≥45
IGT Blister(Top)	m/s	≥1.2
COBB Test(60s) (Top)	g/m ²	≤55
PLY Bonding	J/m ²	≥130

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.